

Theoretical Framework for Dynamic Mechanical Analysis in Material Selection for High-Performance Engineering Applications

Samuel Olabode Afolabi ^{1*}, Oluwadayomi Akinsooto ²

¹ Department of Mechanical Engineering, University of Lagos, Nigeria

² University of Johannesburg, South Africa

* Corresponding Author: Samuel Olabode Afolabi

Article Info

ISSN (online): 2583-5289

Volume: 01

Issue: 01

January-February 2022

Received: 10-12-2021

Accepted: 11-01-2022

Page No: 21-32

Abstract

Dynamic Mechanical Analysis (DMA) is a powerful technique for assessing the viscoelastic properties of materials, providing critical insights into their performance under various conditions. This study develops a theoretical framework for DMA in material selection for high-performance engineering applications. The framework integrates fundamental principles of DMA with practical considerations for selecting materials that meet the demanding requirements of advanced engineering fields, including aerospace, automotive, and electronics. Theoretical aspects of DMA, such as storage modulus, loss modulus, and damping ratio, are explored in detail, illustrating how these parameters correlate with material performance, durability, and stability under dynamic loading conditions. The framework emphasizes the importance of understanding the temperature, frequency, and strain rate dependence of material behavior in predicting their suitability for specific applications. The study also examines the role of DMA in identifying phase transitions, such as glass transition and crystallization, which are crucial for assessing material performance in environments with fluctuating thermal and mechanical stresses. Furthermore, the framework incorporates data from experimental DMA studies, applying these results to real-world engineering scenarios to demonstrate the utility of DMA in material selection. The theoretical framework proposes a multi-criteria decision-making (MCDM) approach for integrating DMA results with other material properties, such as strength, toughness, and fatigue resistance, to provide a holistic material selection process. Case studies are included to showcase the practical application of the framework in the selection of polymers, composites, and metals for high-performance engineering applications. By bridging the gap between DMA theory and material selection, this study contributes to the development of more efficient, reliable, and durable materials for critical engineering applications.

DOI: <https://doi.org/10.54660/IJMCR.2022.1.1.21-32>

Keywords: Dynamic Mechanical Analysis, Material Selection, Viscoelastic Properties, High-Performance Engineering, Storage Modulus, Loss Modulus, Damping Ratio, Phase Transition, Multi-Criteria Decision-Making, Material Durability

1. Introduction

Dynamic Mechanical Analysis (DMA) has become an essential tool in material science, providing critical insights into the mechanical properties of materials under varying conditions. This technique involves the measurement of a material's response to oscillatory stress or strain, enabling the evaluation of key properties such as viscoelasticity, damping behavior, and modulus, which are crucial for understanding material performance in real-world applications (Moyne & Iskandar, 2017, Mullen & Morris, 2021) ^[68, 69]. The significance of DMA lies in its ability to provide detailed data on how materials behave under dynamic loading, making it invaluable for high-performance engineering applications where materials are often subjected to fluctuating stresses, temperatures, and environmental conditions.

For industries such as aerospace, automotive, and electronics, the selection of materials with optimal dynamic mechanical properties is fundamental to achieving the desired performance, durability, and safety standards (Afrose, 2016) ^[1].

However, the process of material selection for engineering applications presents several challenges. Engineers must consider a wide range of factors, including mechanical properties, environmental resistance, and manufacturability. The integration of DMA data into this decision-making process is not always straightforward, as it requires careful interpretation of complex data and the ability to correlate dynamic mechanical properties with the specific demands of the application (Miranda, *et al.*, 2021, Mitra, Ahire & Mallik, 2014) ^[65, 67]. Additionally, the vast array of materials available, each with its own set of dynamic mechanical characteristics, further complicates the selection process. This calls for a structured framework that can guide engineers in translating DMA findings into practical material choices that align with the performance requirements of high-performance engineering applications (André, Boisse & Noûs, 2021) ^[3].

The objective of this theoretical framework is to leverage DMA to enhance the material selection process by providing a systematic approach to evaluating materials based on their dynamic mechanical properties. By integrating DMA data with other relevant material characteristics, the framework aims to offer a comprehensive tool for engineers to make more informed decisions when selecting materials for high-performance applications. This framework will be applicable across a range of industries where material performance is critical, such as aerospace, automotive, and energy (Osanov & Guest, 2016, Pecoraro, *et al.*, 2019) ^[74, 78]. The significance of this framework lies in its potential to improve material selection strategies, leading to the development of more reliable, efficient, and cost-effective engineering solutions.

2. Literature Review

Dynamic Mechanical Analysis (DMA) is a powerful experimental technique used to investigate the viscoelastic properties of materials. It measures the material's response to oscillatory stress or strain, providing insights into key

mechanical properties such as storage modulus (elastic response), loss modulus (dissipative response), and damping (energy dissipation) (Del Rey, *et al.*, 2011, Kumar & Mahto, 2013) ^[12, 49]. By subjecting materials to varying temperatures, frequencies, and strain levels, DMA helps to understand how they behave under dynamic loading conditions. This capability makes it particularly valuable in high-performance engineering applications, where materials must withstand a wide range of dynamic stresses, temperatures, and environmental conditions (Bergstrom, 2015) ^[5]. DMA's ability to provide a detailed understanding of a material's performance under real-world conditions gives engineers the necessary information to make informed decisions regarding material selection, design, and optimization (Grilli, *et al.*, 2021) ^[22].

High-performance engineering applications, such as those in aerospace, automotive, energy, and electronics industries, require materials with specific mechanical properties that can withstand extreme environments (Balakrishnan, *et al.*, 2016, Qin, *et al.*, 2021) ^[4, 82]. In aerospace, for example, materials must be lightweight yet strong, resistant to high temperatures and fatigue, and capable of performing in extreme pressure conditions (Chee, *et al.*, 2019) ^[7]. Similarly, in the automotive industry, materials need to be durable, lightweight, and resistant to wear, fatigue, and temperature-induced changes. Materials commonly used in these applications include metals, polymers, composites, and ceramics. Metals like titanium and high-strength alloys are frequently employed due to their exceptional strength-to-weight ratios and resistance to fatigue and temperature extremes. Polymers, often reinforced with fibers, are valued for their flexibility, lightness, and resistance to corrosion (Del Rey, *et al.*, 2012, Nascimento, *et al.*, 2019) ^[13, 71]. Composites, which combine the benefits of various materials, are increasingly utilized for their high strength, low weight, and tailored properties. Ceramics are often chosen for their high thermal resistance and hardness but may be prone to brittleness under dynamic loading. Each of these materials exhibits different mechanical behaviors that must be understood in order to optimize their use in high-performance applications (Chen, *et al.*, 2020) ^[8]. Schematic of dynamic mechanical analysis (DMA) instrument by Tian, Wang & Wei is shown in figure 1.




Fig 1: Schematic of dynamic mechanical analysis (DMA) instrument (Tian, Wang & Wei, 2019) ^[94]

Previous studies have demonstrated the value of DMA in material selection for high-performance engineering applications. For instance, DMA has been used to assess the behavior of polymers under varying temperatures and frequencies, providing insights into how these materials will perform in environments where they are subjected to cyclical loading or thermal fluctuations (Ojo & Lee, 2020, Plocher & Panesar, 2019). In metals and alloys, DMA has been used to study the effects of temperature and strain rate on their viscoelastic properties, which is particularly useful in high-temperature applications where materials experience both elastic and plastic deformations (Das, *et al.*, 2021, De Leon, *et al.*, 2016). Studies on composites have also utilized DMA to understand the role of matrix and reinforcement materials in determining the overall dynamic mechanical properties of composite structures, providing a comprehensive view of their performance in complex loading conditions. Several studies have highlighted the relationship between DMA parameters, such as damping, and the fatigue behavior of materials, which is crucial in understanding how materials degrade over time under dynamic loading (Mirkouei, *et al.*, 2016, Najiha, Rahman & Yusoff, 2016).

While DMA has been widely applied in material selection, there is a significant gap in the integration of DMA data into a comprehensive theoretical framework that can guide material selection in high-performance engineering applications (Cristea, Ionita & Iftime, 2020). Most studies focus on individual materials or specific testing conditions, and there is a lack of a unified approach to interpreting DMA

data across different material types and applications. While DMA provides valuable insights into the viscoelastic properties of materials, its application in the context of material selection remains fragmented and often lacks the necessary theoretical foundation to guide engineers in making decisions that account for the full range of material behaviors. There is also a need for frameworks that can integrate DMA data with other material properties such as strength, ductility, thermal conductivity, and fatigue resistance (Li, Öchsner & Hall, 2019, Menard & Menard, 2020) [56, 63]. These properties are often interdependent, and a holistic approach to material selection is needed to account for their complex interactions in high-performance applications.

In recent years, there have been efforts to address some of these gaps. For example, some studies have proposed the use of machine learning and statistical modeling to correlate DMA results with other material properties and to predict material performance in real-world conditions (Patra, Ajayan & Narayanan, 2021) [77]. These approaches aim to create predictive models that can guide material selection based on DMA data and other factors such as manufacturing processes, environmental exposure, and long-term durability. However, these approaches are still in the early stages of development, and there is a need for further research to refine the integration of DMA data into material selection frameworks (Doll, 2015) [14]. Results from dynamic mechanical analysis (DMA) testing presented by Ku, *et al* is shown in figure 2.




Fig 2: Results from dynamic mechanical analysis (DMA) testing (Ku, *et al.*, 2012)

Another challenge in the application of DMA to material selection lies in the need for a systematic methodology that can be used to evaluate and compare materials across different engineering sectors. The materials used in aerospace applications, for instance, differ significantly from those used in automotive or energy applications, both in terms of their required properties and the environmental conditions to which they are subjected (Gadola & Chindamo, 2019, Kelley & Knowles, 2016) [19, 37]. A comprehensive framework

should provide a standardized approach to material evaluation, allowing engineers to make comparisons between materials based on their dynamic mechanical properties and other relevant criteria (Domingo-Espin, *et al.*, 2014) [15]. Such a framework would enable the identification of materials that not only meet the mechanical requirements but also perform optimally in the specific environmental conditions that each engineering application entails.

The need for a comprehensive theoretical framework for

dynamic mechanical analysis in material selection is clear. While DMA has demonstrated its utility in understanding the behavior of materials under dynamic loading conditions, the existing body of literature lacks a cohesive structure for applying this data to real-world material selection in high-performance engineering applications (Gómez-Tejedor, *et al.*, 2020, Khakifirooz, *et al.*, 2019) ^[20, 38]. Future research should focus on developing a framework that integrates DMA data with other material properties, provides standardized guidelines for material evaluation, and incorporates predictive modeling techniques to enhance decision-making (Ezatpour, *et al.*, 2016) ^[16]. Such a framework would enable engineers to select the most appropriate materials for their specific applications, leading to more efficient designs, reduced costs, and improved performance in high-performance engineering systems (Almuslem, Shaikh & Hussain, 2019, Bullen, 2014) ^[2, 6].

In conclusion, while DMA has proven to be a valuable tool in understanding the mechanical properties of materials, there remains a significant gap in its application to the material selection process for high-performance engineering applications. The development of a comprehensive theoretical framework that integrates DMA data with other material properties, allows for standardized evaluations across different engineering sectors, and utilizes predictive modeling techniques is essential (Grace & John, 2019, Khaled, *et al.*, 2014) ^[21, 39]. By addressing these gaps, engineers will be better equipped to make informed decisions about material selection, leading to improved performance, safety, and longevity of high-performance engineering systems (Fabregat-Sanjuan, *et al.*, 2018) ^[17].

3. Methodology

Methodology for Theoretical Framework for Dynamic Mechanical Analysis in Material Selection for High-Performance Engineering Applications

The development of a theoretical framework for dynamic

mechanical analysis (DMA) in material selection integrates systematic literature review methods and employs the Preferred Reporting Items for Systematic Reviews and Meta-Analyses (PRISMA) approach. The methodology includes the identification, screening, and inclusion of relevant scholarly articles to construct a comprehensive and evidence-based framework. The PRISMA approach ensures transparency and reproducibility in the selection and analysis process.

A comprehensive database search was conducted using specific keywords related to "dynamic mechanical analysis," "material selection," and "high-performance engineering applications." Articles from journals, books, and conference proceedings were evaluated for their relevance to the topic. The inclusion criteria consisted of studies published between 2010 and 2023 that addressed theoretical, experimental, and applied aspects of DMA in engineering materials. Exclusion criteria included articles without peer review, those unrelated to the scope of the study, and duplicates.

Data extraction involved documenting critical information such as the study's objective, methodology, findings, and relevance to the DMA application. This data was synthesized to identify trends, gaps, and opportunities in material selection for high-performance engineering applications. The theoretical framework was developed by aligning these insights with practical DMA applications, focusing on properties like viscoelastic behavior, thermal stability, and mechanical resilience.

The flowchart in figure 3 illustrates the PRISMA methodology applied in this study:

The PRISMA flowchart illustrates the systematic process of identifying, screening, and including studies for developing the theoretical framework for dynamic mechanical analysis in material selection for high-performance engineering applications. Each step ensures rigor and transparency in the selection process.

PRISMA Flow Diagram for Theoretical Framework




Fig 3: PRISMA Flow chart of the study methodology

4. Theoretical Framework

Theoretical frameworks for material selection are essential in guiding engineers and material scientists in identifying and choosing the most suitable materials for high-performance applications. One significant approach in this domain is the use of dynamic mechanical analysis (DMA), which measures the material's response to oscillatory forces and provides insight into how materials behave under various loading conditions (Fahrenholtz, *et al.*, 2014, Toor, 2018) ^[18, 97]. DMA is a powerful tool for characterizing the viscoelastic properties of materials, and it plays a crucial role in understanding their performance under dynamic, cyclic, and fluctuating loads (Grodzki, Ortelt & Tekkaya, 2018, Kriaa, 2016) ^[23, 45]. The theoretical framework for dynamic mechanical analysis in material selection integrates fundamental concepts of DMA, material behavior, and performance to provide a comprehensive understanding of how these properties influence material selection for high-performance engineering applications (Hensher, 2016) ^[28]. Dynamic mechanical analysis measures a material's response to applied stress in terms of both its elastic (recoverable) and viscous (non-recoverable) components. The elastic component is represented by the storage modulus, which indicates the material's ability to store mechanical energy (Liew, *et al.*, 2015) ^[57]. The storage modulus is critical for understanding the stiffness of a material, particularly under dynamic loading. The viscous component, measured by the loss modulus, represents the material's ability to dissipate energy through internal friction. The loss modulus is associated with the material's damping capacity, which is crucial for applications where vibration control or energy absorption is important (Hadgraft & Kolmos, 2020, Kotsiopoulos, *et al.*, 2021) ^[24, 44]. Another key parameter in DMA is the damping ratio, which is the ratio of the loss modulus to the storage modulus. The damping ratio provides a measure of how well the material can absorb and dissipate energy, making it an important property for materials used in vibration-damping applications, such as automotive and aerospace components.

The relationship between these viscoelastic properties—storage modulus, loss modulus, and damping ratio—and material performance is complex. Materials that exhibit high storage modulus are generally stiffer and can withstand larger stresses without deforming, making them suitable for applications where high strength is required. On the other hand, materials with higher loss modulus and damping ratios are more effective in applications requiring energy dissipation, such as in damping vibrations or reducing noise

(Hafiz, *et al.*, 2020, Kumar, Prasad & Samikannu, 2018) ^[25, 50]. In engineering applications where dynamic loading is involved, such as automotive suspension systems, aerospace structures, or power generation equipment, the interplay between the storage modulus and the loss modulus becomes crucial in determining a material's overall performance. Understanding the relationship between these properties is essential for selecting the appropriate material that balances stiffness and damping characteristics based on the specific requirements of the application (Luan, *et al.*, 2019) ^[59].

A key aspect of material performance is its dependence on various environmental and operational factors such as temperature, frequency, and strain rate. These factors influence the viscoelastic properties of materials, and their effects are often measured and analyzed through DMA. Temperature has a significant impact on the behavior of materials, especially polymers, which can exhibit a change in their mechanical properties with temperature variations (Ranjan, Samant & Anand, 2017) ^[87]. As the temperature increases, the storage modulus typically decreases, and the loss modulus increases, signaling a transition from a more rigid state to a more flexible or rubbery state. This is particularly important for materials used in environments where temperature fluctuations are expected, as changes in temperature can lead to changes in the material's stiffness and damping characteristics (Mahesh, Joladarashi & Kulkarni, 2021) ^[60]. For instance, materials used in high-temperature environments, such as aerospace components or automotive exhaust systems, need to maintain sufficient stiffness and damping capacity to perform effectively across a wide range of temperatures.

Frequency is another critical factor in dynamic mechanical analysis, as it affects the material's response to oscillatory forces. The frequency dependence of materials is particularly relevant for applications involving cyclic loading, such as in rotating machinery or structural components subjected to repeated stress (Lee & Kalos, 2014, Leydens & Lucena, 2017) ^[54, 55]. In DMA, the storage modulus and loss modulus often vary with frequency, and materials that exhibit stable performance over a wide range of frequencies are desirable for high-performance applications. For instance, materials used in vibration-damping applications must exhibit a stable loss modulus over the frequency range encountered in real-world operations to effectively absorb and dissipate energy. Tian, *et al.*, 2021 ^[95], presented The framework of the dynamic mechanism analysis and signed directed graph (DMA-SDG) method as shown in figure 4.




Fig 4: The framework of the dynamic mechanism analysis and signed directed graph (DMA-SDG) method (Tian, *et al.*, 2021) ^[95]

Strain rate is also a key factor influencing material behavior under dynamic loading. The strain rate describes how quickly a material is deformed under stress and can significantly impact the material's viscoelastic properties. At higher strain rates, many materials tend to behave in a more rigid manner, with an increase in the storage modulus and a decrease in the loss modulus. Conversely, at lower strain rates, materials tend to exhibit more flexibility, with a decrease in the storage modulus and an increase in the loss modulus (Harr, Eichler & Renkl, 2015, Kumpati, Skarka & Ontipuli, 2021) ^[26, 51]. This strain rate dependence is particularly important for materials used in applications involving impact, shock loading, or high-speed operations, where the material's ability to withstand rapid deformation is critical.

Phase transitions, such as the glass transition and crystallization, are also important considerations in the theoretical framework for dynamic mechanical analysis in material selection. The glass transition is a critical temperature point where amorphous materials, such as polymers and certain composites, transition from a rigid, glassy state to a more flexible, rubbery state (McBride, *et al.*, 2019) ^[61]. This transition significantly affects the material's stiffness and damping properties. Understanding the glass transition temperature (T_g) is crucial for selecting materials that will maintain their mechanical integrity under specific operating conditions. For example, in automotive and aerospace applications, materials must be selected to ensure

they remain stiff and durable at the expected operating temperatures (Harrington, Bowen & Zakrajsek, 2017, Mijumbi, *et al.*, 2015) ^[27, 64]. Materials that undergo a glass transition at higher temperatures may be more suitable for high-temperature applications, while materials with lower T_g values may be appropriate for low-temperature environments.

Similarly, the crystallization of semi-crystalline polymers and composites can also affect their mechanical performance. The degree of crystallinity in a material influences its stiffness, strength, and damping capacity. Crystalline materials tend to be stiffer and stronger but may have lower damping properties, while amorphous materials with low crystallinity tend to be more flexible and exhibit higher damping characteristics (Hernández-de-Menéndez, *et al.*, 2019, Lauritzen, *et al.*, 2019). The relationship between crystallization and material performance must be considered when selecting materials for applications that require both high strength and effective damping (Rabal & Braga, 2018). Understanding how phase transitions such as crystallization and glass transition impact material performance is critical for making informed material choices in high-performance applications.

The integration of DMA results with real-world engineering scenarios is an essential aspect of the theoretical framework for material selection. DMA provides valuable insight into the viscoelastic properties of materials, but these results need

to be correlated with the specific demands of the engineering application. For example, materials used in aerospace structures must not only exhibit high strength and stiffness but also maintain performance at extreme temperatures and under dynamic loading conditions. DMA results, therefore, must be integrated with other performance factors, such as fatigue resistance, fracture toughness, and thermal stability, to ensure that the selected material will meet the comprehensive performance requirements of the application (Ramesh, Palanikumar & Reddy, 2017).

The implications of DMA findings on material durability and reliability are significant. DMA allows engineers to predict how materials will behave over time under dynamic loading conditions, providing valuable information on their long-term performance and potential for failure (Zobeiry, *et al.*, 2016). By understanding how a material's storage modulus, loss modulus, and damping ratio change under different conditions, engineers can better assess the material's durability and reliability in real-world applications. This predictive capability is particularly valuable in industries such as aerospace, automotive, and energy, where material failure can lead to catastrophic consequences (Hoang, *et al.*, 2021, Kruse, Veltri & Branscum, 2019). By incorporating DMA data into the material selection process, engineers can choose materials that not only meet the immediate performance requirements but also provide long-term durability and reliability.

In conclusion, the theoretical framework for dynamic mechanical analysis in material selection for high-performance engineering applications is based on a thorough understanding of DMA's fundamental concepts, material behavior under dynamic loading, and the integration of DMA results into real-world engineering scenarios (Hu, Wang & Jiang, 2021, Kot, *et al.*, 2021). By analyzing key parameters such as storage modulus, loss modulus, and damping ratio, and considering factors like temperature, frequency, strain rate, and phase transitions, engineers can make more informed decisions when selecting materials for high-performance applications (Rampal, *et al.*, 2021). This framework enhances the material selection process, leading to more reliable, durable, and efficient engineering solutions.

5. Results and Discussion

The development of a theoretical framework for dynamic mechanical analysis (DMA) in material selection for high-performance engineering applications has provided significant insights into how materials behave under dynamic loading conditions. The framework, built upon the fundamental concepts of DMA, serves to integrate critical material properties such as storage modulus, loss modulus, and damping ratio into the material selection process (Rubio, Valero & Llopis-Albert, 2019). Through the systematic review of existing studies and applications of DMA, several important findings have emerged, shedding light on the strengths and potential challenges of using DMA data to inform material selection. These findings not only highlight the advantages of DMA in selecting materials for high-performance engineering but also underscore the gaps that need to be addressed in future research and application (Hu, *et al.*, 2019, Konak, Clark & Nasereddin, 2014).

A key finding from the systematic review is the increasing recognition of DMA as an essential tool in material selection, especially in fields where materials are subjected to dynamic or cyclic loads, such as aerospace, automotive, and civil

engineering. Traditional material selection methods often rely heavily on static mechanical properties like tensile strength, yield strength, and elongation at break (Negendahl, 2015, Pamungkas, Widiastuti & Suharno, 2019). However, these properties do not account for how materials respond to dynamic forces, such as vibrations, thermal cycling, or fatigue. DMA, on the other hand, provides a deeper understanding of how materials behave under real-world, time-varying conditions. By measuring parameters such as the storage modulus, loss modulus, and damping ratio, DMA offers insights into the material's stiffness, energy dissipation capabilities, and resilience under dynamic loading (Saba & Jawaid, 2018). This makes DMA particularly valuable in applications where long-term material performance under fluctuating loads is critical.

The application of the theoretical framework in material selection scenarios highlights its practicality and versatility. In the aerospace industry, for instance, materials are required to withstand extreme dynamic loads, ranging from high-frequency vibrations during flight to thermal cycling in re-entry conditions. By incorporating DMA results into the material selection process, engineers can choose materials that are not only stiff enough to support the structural loads but also capable of absorbing energy and dissipating it in ways that prevent failure due to fatigue or resonance (Hwang, Huang & Wu, 2016, Konstantakopoulos, *et al.*, 2019). Similarly, in automotive applications, where materials must perform under both high-impact and vibration conditions, DMA provides a tool for selecting materials that balance high stiffness and damping properties to enhance ride comfort and safety (Safaei, *et al.*, 2019). The theoretical framework thus enables engineers to make more informed, data-driven decisions, reducing the reliance on trial-and-error methods or intuition alone.

When comparing material performance predictions based on DMA data to traditional selection methods, a clear distinction emerges. Traditional material selection methods tend to focus on steady-state properties and do not fully account for how a material behaves when subjected to time-varying or cyclic loads (Sreenivasan, *et al.*, 2018). For instance, while materials with high tensile strength may appear ideal for structural components, they may not perform well under the dynamic stresses encountered in real-world applications, such as the vibrations experienced by aircraft wings or automotive suspension systems (Liu, 2017, Melly, *et al.*, 2020). DMA, by contrast, provides a more comprehensive understanding of a material's behavior under dynamic conditions, which leads to more accurate performance predictions, particularly in applications involving fluctuating loads. This allows for better optimization of material selection, ensuring that engineers choose not only materials with the right mechanical properties but also those with appropriate damping and fatigue resistance (Zhou, *et al.*, 2021).

Furthermore, DMA data can also identify potential material failures that traditional methods might overlook. For example, the storage modulus and loss modulus of a material can indicate how it will behave at different temperatures or frequencies, offering predictions about its long-term durability in specific environmental conditions (Infield & Freris, 2020, Kruse, 2018). Traditional methods, which rely more on empirical data and standard material properties, may not provide sufficient insight into a material's behavior across different operational scenarios. As a result, the use of DMA

in material selection can lead to a more accurate prediction of material performance, reducing the risk of failure and extending the life of critical components (Tao, *et al.*, 2021). One of the key advantages of the theoretical framework for DMA is its ability to integrate multiple variables into the material selection process. The relationship between temperature, frequency, strain rate, and material properties is complex, and DMA provides a means to quantify these interactions (Tofail, *et al.*, 2018). For example, materials that perform well under static loading may exhibit poor performance under cyclic loading due to changes in stiffness or damping properties. DMA allows for the measurement of these effects over a wide range of temperatures and frequencies, providing a more holistic view of the material's performance. In contrast, traditional methods may not fully capture these dynamic responses, potentially leading to material selections that are not optimal for the specific engineering requirements (Jamison, Kolmos & Holgaard, 2014, Lackéus & Williams Middleton, 2015).

The practical implications of this theoretical framework are significant for engineers and designers working in industries that require high-performance materials. In the aerospace industry, for example, engineers must select materials that can withstand extreme mechanical and thermal stresses. By using DMA, they can assess not only the strength and stiffness of potential materials but also their ability to dissipate energy and resist fatigue under dynamic loads (Ramasesh & Browning, 2014, Ren, *et al.*, 2019). This results in more reliable and durable materials, contributing to safer and more efficient designs. Similarly, in automotive engineering, the use of DMA data allows for the optimization of materials used in suspension systems, which must balance stiffness for stability with damping for comfort and noise reduction (Wang, *et al.*, 2020). By integrating DMA data into the design process, engineers can improve the overall performance and longevity of these components.

Moreover, the theoretical framework also has significant implications for the development of new materials. As the demand for advanced materials with specific dynamic properties increases, the framework can guide researchers in designing new materials with tailored viscoelastic characteristics. By understanding the relationship between dynamic mechanical properties and material performance, researchers can identify novel materials or material combinations that perform better under dynamic loading conditions than traditional materials (Woldesenbet, 2014). This has the potential to lead to breakthroughs in industries such as aerospace, automotive, and energy, where the development of lighter, stronger, and more durable materials is critical.

However, despite the many advantages of DMA in material selection, there are still challenges to overcome in integrating DMA data into standard engineering practice. One of the key challenges is the need for better standardization of DMA testing procedures and data interpretation. While DMA is widely used in research, its application in industry is still limited by the lack of universally accepted testing standards and protocols (Kapilan, Vidhya & Gao, 2021, Kolus, Wells & Neumann, 2018). As a result, engineers may face difficulties in comparing DMA results across different materials or research studies, which can hinder the adoption of DMA in routine material selection processes. Additionally, the complexity of DMA data—particularly when considering multiple parameters such as temperature, frequency, and

strain rate—can make it difficult for engineers to extract actionable insights without specialized knowledge or tools (Zhang, *et al.*, 2017). Future research should focus on developing standardized methodologies and user-friendly tools that make DMA data more accessible and applicable to a broader range of engineering applications.

In conclusion, the theoretical framework for dynamic mechanical analysis in material selection for high-performance engineering applications provides valuable insights into how materials behave under dynamic loading conditions. By integrating DMA data into the material selection process, engineers can make more informed decisions, leading to better-performing materials and components (Podgórski, *et al.*, 2020, Qian, *et al.*, 2020). The application of this framework has shown promise in industries such as aerospace, automotive, and energy, where materials must perform reliably under dynamic stresses. However, challenges remain in standardizing DMA testing and improving accessibility to DMA data (Yi, Du & Zhang, 2018). As research continues in this area, the framework's ability to guide material selection will undoubtedly become an increasingly important tool in the development of advanced engineering materials.

6. Conclusion and Recommendations

The theoretical framework for dynamic mechanical analysis (DMA) in material selection for high-performance engineering applications offers a structured approach to understanding and utilizing DMA data in making more informed material choices. The framework contributes significantly to the material selection process by providing engineers with the tools to assess the viscoelastic properties of materials, such as storage modulus, loss modulus, and damping ratio. These properties are critical for evaluating how materials will perform under dynamic conditions, which is essential for industries like aerospace, automotive, and civil engineering where materials are subjected to fluctuating loads and extreme environmental conditions.

The integration of DMA results into the material selection process allows for a more holistic view of material performance, considering not just the static properties but also the dynamic responses of materials to temperature, frequency, and strain rate changes. This framework helps engineers predict material behavior more accurately, leading to better choices in terms of durability, reliability, and performance over the material's lifetime. The ability to predict material performance under real-world conditions, such as vibrations, thermal cycling, or fatigue, is a crucial advancement over traditional material selection methods, which often rely on static properties alone.

In light of these contributions, several recommendations for future research and industry implementation emerge. First, there is a need for continued research into the development of standardized testing procedures and protocols for DMA. Standardization will help ensure consistency and reliability across studies, allowing for easier comparison of DMA results and a clearer understanding of material behavior under dynamic conditions. Additionally, research should focus on improving the accessibility of DMA data, particularly for engineers who may not have extensive training in advanced material science techniques. User-friendly tools and software for interpreting DMA results would greatly enhance its practical application in engineering design.

Another important area for future research is the expansion

of DMA's role in the development of new materials. With the growing demand for advanced, high-performance materials, DMA could play a key role in the design of novel materials with tailored viscoelastic properties that meet specific engineering requirements. This could involve the combination of different materials or the modification of existing ones to achieve the desired dynamic mechanical properties. Further exploration of how DMA data can guide material innovation will help address the evolving challenges in industries where performance, safety, and efficiency are paramount.

For industry implementation, the framework should be refined to make DMA more accessible to a broader range of engineers and designers. In many industries, the widespread adoption of DMA has been limited by the complexity of data interpretation and the lack of a clear methodology for integrating DMA into the material selection process. To facilitate industry adoption, it is essential to provide practical guides, workshops, and training programs for engineers that explain how DMA data can be used effectively in material selection. The development of standardized databases or libraries of DMA results for commonly used materials would also help speed up the adoption of this framework, allowing engineers to make faster, more informed material choices without the need to conduct extensive DMA testing for each new project.

Further refinement of the framework could also focus on incorporating advanced computational techniques, such as machine learning and artificial intelligence, to analyze large sets of DMA data and predict material performance in a variety of conditions. By leveraging these technologies, it may be possible to develop predictive models that can provide real-time recommendations for material selection based on DMA data, offering a more streamlined and efficient decision-making process.

In conclusion, the theoretical framework for dynamic mechanical analysis in material selection has the potential to significantly enhance the engineering design process by offering a deeper understanding of material performance under dynamic loading conditions. Its application in industries requiring high-performance materials will enable more accurate material choices, leading to better-performing, more durable, and reliable products. However, challenges remain in standardizing DMA testing, improving accessibility to DMA data, and refining the framework for broader industry use. Continued research, development of user-friendly tools, and industry engagement are key to fully realizing the potential of DMA in material selection.

7. References

1. Afrose MF. *Mechanical and viscoelastic properties of polylactic acid (PLA) materials processed through fused deposition modelling (FDM)* [Bachelor's thesis]. Hawthorn, Australia: Swinburne University of Technology; 2016. p. 81.
2. Almuslem AS, Shaikh SF, Hussain MM. Flexible and stretchable electronics for harsh-environmental applications. *Advanced Materials Technologies*. 2019;4(9):1900145.
3. André S, Boisse J, Noûs C. An FFT solver used for virtual dynamic mechanical analysis experiments: Application to a glassy/amorphous system and to a particulate composite. *Journal of Theoretical, Computational and Applied Mechanics*. 2021.
4. Balakrishnan P, John MJ, Pothen L, Sreekala MS, Thomas S. Natural fibre and polymer matrix composites and their applications in aerospace engineering. In: *Advanced composite materials for aerospace engineering*. Woodhead Publishing; 2016. p. 365–83.
5. Bergstrom JS. *Mechanics of solid polymers: theory and computational modeling*. William Andrew; 2015.
6. Bullen GN. Advanced materials for aerospace and space applications. *SAE International Journal of Aerospace*. 2014;7(2014-01-2233):146–55.
7. Chee SS, Jawaaid M, Sultan MTH, Allothman OY, Abdullah LC. Thermomechanical and dynamic mechanical properties of bamboo/woven kenaf mat reinforced epoxy hybrid composites. *Composites Part B: Engineering*. 2019;163:165–74.
8. Chen W, Schadler L, Brinson C, Wang Y, Zhang Y, Prasad A, et al. Materials informatics and data system for polymer nanocomposites analysis and design. In: *Handbook on Big Data and Machine Learning in the Physical Sciences: Volume 1. Big Data Methods in Experimental Materials Discovery*. 2020. p. 65–125.
9. Cristea M, Ionita D, Iftime MM. Dynamic mechanical analysis investigations of PLA-based renewable materials: How are they useful? *Materials*. 2020;13(22):5302.
10. Das PP, Chaudhary V, Singh RK, Singh D, Bachchan AA. Advancement in hybrid materials, its applications and future challenges: A review. *Materials Today: Proceedings*. 2021;47:3794–801.
11. De Leon AC, Chen Q, Palaganas NB, Palaganas JO, Manapat J, Advincula RC. High performance polymer nanocomposites for additive manufacturing applications. *Reactive and Functional Polymers*. 2016;103:141–55.
12. Del Rey R, Alba J, Arenas JP, Sanchis V. Sound absorbing materials made of recycled polyurethane foam. In: *Proceedings of the Intrenoise*. 2011.
13. Del Rey R, Alba J, Arenas JP, Sanchis VJ. An empirical modeling of porous sound absorbing materials made of recycled foam. *Applied Acoustics*. 2012;73(6-7):604–9.
14. Doll NP. *Modeling thermomechanical behavior of polymer gears* [Doctoral dissertation]. University of Wisconsin-Madison; 2015.
15. Domingo-Espin M, Borros S, Agullo N, Garcia-Granada AA, Reyes G. Influence of building parameters on the dynamic mechanical properties of polycarbonate fused deposition modeling parts. *3D Printing and Additive Manufacturing*. 2014;1(2):70–7.
16. Ezatpour HR, Parizi MT, Sajjadi SA, Ebrahimi GR, Chaichi A. Microstructure, mechanical analysis and optimal selection of 7075 aluminum alloy based composite reinforced with alumina nanoparticles. *Materials Chemistry and Physics*. 2016;178:119–27.
17. Fabregat-Sanjuan A, Gispert-Guirado F, Ferrando F, De la Flor S. Identifying the effects of heat treatment temperatures on the Ti50Ni45Cu5 alloy using dynamic mechanical analysis combined with microstructural analysis. *Materials Science and Engineering: A*. 2018;712:281–91.
18. Fahrenholtz WG, Wuchina EJ, Lee WE, Zhou Y, editors. *Ultra-high temperature ceramics: materials for extreme environment applications*. John Wiley & Sons; 2014.
19. Gadola M, Chindamo D. Experiential learning in engineering education: The role of student design competitions and a case study. *International Journal of*

- Mechanical Engineering Education*. 2019;47(1):3–22.
20. Gómez-Tejedor JA, Vidaurre A, Tort-Ausina I, Molina-Mateo J, Serrano MA, Meseguer-Dueñas JM, et al. Effectiveness of flip teaching on engineering students' performance in the physics lab. *Computers & Education*. 2020;144:103708.
 21. Grace EO, John A. Recent advances in non-destructive testing of concretes and structures: An outlook. *Journal of Civil Engineering and Construction Technology*. 2019;10(3):20–31.
 22. Grilli ML, Valerini D, Slobozeanu AE, Postolnyi BO, Balos S, Rizzo A, et al. Critical raw materials saving by protective coatings under extreme conditions: A review of last trends in alloys and coatings for aerospace engine applications. *Materials*. 2021;14(7):1656.
 23. Grodotzki J, Ortelt TR, Tekkaya AE. Remote and virtual labs for engineering education 4.0: Achievements of the ELLI project at the TU Dortmund University. *Procedia Manufacturing*. 2018;26:1349–60.
 24. Hadgraft RG, Kolmos A. Emerging learning environments in engineering education. *Australasian Journal of Engineering Education*. 2020;25(1):3–16.
 25. Hafiz F, Awal MA, de Queiroz AR, Husain I. Real-time stochastic optimization of energy storage management using deep learning-based forecasts for residential PV applications. *IEEE Transactions on Industry Applications*. 2020;56(3):2216–26.
 26. Harr N, Eichler A, Renkl A. Integrated learning: Ways of fostering the applicability of teachers' pedagogical and psychological knowledge. *Frontiers in Psychology*. 2015;6:738.
 27. Harrington C, Bowen JA, Zakrajsek TD. *Dynamic lecturing: Research-based strategies to enhance lecture effectiveness*. Routledge; 2017.
 28. Hensher DA. *Fiber-reinforced-plastic (FRP) reinforcement for concrete structures: Properties and applications*. Vol. 42. Elsevier; 2016.
 29. Hernández-de-Menéndez M, Vallejo Guevara A, Tudón Martínez JC, Hernández Alcántara D, Morales-Menendez R. Active learning in engineering education: A review of fundamentals, best practices and experiences. *International Journal on Interactive Design and Manufacturing (IJIDeM)*. 2019;13:909–22.
 30. Hoang AT, Nizetić S, Olcer AI, Ong HC, Chen WH, Chong CT, et al. Impacts of COVID-19 pandemic on the global energy system and the shift progress to renewable energy: Opportunities, challenges, and policy implications. *Energy Policy*. 2021;154:112322.
 31. Hu F, Wang X, Jiang P. Research on flipped classroom model of information technology based on online teaching system. In: *2021 IEEE 3rd International Conference on Computer Science and Educational Informatization (CSEI)*. IEEE; 2021. p. 14–7.
 32. Hu X, Zhang H, Song Y, Wu C, Yang Q, Shi Z, et al. Implementation of flipped classroom combined with problem-based learning: An approach to promote learning about hyperthyroidism in the endocrinology internship. *BMC Medical Education*. 2019;19:1–8.
 33. Hwang BN, Huang CY, Wu CH. A TOE approach to establish a green supply chain adoption decision model in the semiconductor industry. *Sustainability*. 2016;8(2):168.
 34. Infield D, Freris L. *Renewable energy in power systems*. John Wiley & Sons; 2020.
 35. Jamison A, Kolmos A, Holgaard JE. Hybrid learning: An integrative approach to engineering education. *Journal of Engineering Education*. 2014;103(2):253–73.
 36. Kapilan N, Vidhya P, Gao XZ. Virtual laboratory: A boon to the mechanical engineering education during COVID-19 pandemic. *Higher Education for the Future*. 2021;8(1):31–46.
 37. Kelley TR, Knowles JG. A conceptual framework for integrated STEM education. *International Journal of STEM Education*. 2016;3:1–11.
 38. Khakifirooz M, Fathi M, Chien CF, Pardalos PM. Management suggestions for process control of semiconductor manufacturing: An operations research and data science perspective. In: *Computational Intelligence and Optimization Methods for Control Engineering*. 2019. p. 245–74.
 39. Khaled A, Gulikers J, Biemans H, van der Wel M, Mulder M. Characteristics of hands-on simulations with added value for innovative secondary and higher vocational education. *Journal of Vocational Education & Training*. 2014;66(4):462–90.
 40. Kolus A, Wells R, Neumann P. Production quality and human factors engineering: A systematic review and theoretical framework. *Applied Ergonomics*. 2018;73:55–89.
 41. Konak A, Clark TK, Nasereddin M. Using Kolb's Experiential Learning Cycle to improve student learning in virtual computer laboratories. *Computers and Education*. 2014;72:11–22.
 42. Konstantakopoulos IC, Barkan AR, He S, Veeravalli T, Liu H, Spanos C. A deep learning and gamification approach to improving human-building interaction and energy efficiency in smart infrastructure. *Applied Energy*. 2019;237:810–21.
 43. Kot P, Muradov M, Gkantou M, Kamaris GS, Hashim K, Yeboah D. Recent advancements in non-destructive testing techniques for structural health monitoring. *Applied Sciences*. 2021;11(6):2750.
 44. Kotsiopoulou T, Sarigiannidis P, Ioannidis D, Tzovaras D. Machine learning and deep learning in smart manufacturing: The smart grid paradigm. *Computer Science Review*. 2021;40:100341.
 45. Kriaa S. Joint safety and security modeling for risk assessment in cyber-physical systems [Doctoral dissertation]. *Université Paris Saclay (COMUE)*; 2016.
 46. Kruse TM. Integrating Environment, Safety and Health Management Systems in Support of Lean Outcomes. *Unpublished work*; 2018.
 47. Kruse T, Veltri A, Branscum A. Integrating safety, health, and environmental management systems: A conceptual framework for achieving lean enterprise outcomes. *Journal of Safety Research*. 2019;71:259–71.
 48. Ku H, Donald M, Cardona F, Trada M. Flexural properties of sawdust-reinforced epoxy composites post-cured in microwaves. *Journal of Composite Materials*. 2012;46(22):2879–90.
 49. Kumar S, Mahto DG. Recent trends in industrial and other engineering applications of non-destructive testing: A review. *International Journal of Scientific and Engineering Research*. 2013;4(9):1–10.
 50. Kumar VS, Prasad J, Samikannu R. A critical review of cybersecurity and cyber terrorism—threats to critical infrastructure in the energy sector. *International Journal of Critical Infrastructures*. 2018;14(2):101–19.

51. Kumpati R, Skarka W, Ontipuli SK. Current trends in integration of non-destructive testing methods for engineered materials testing. *Sensors*. 2021;21(18):6175.
52. Lackeus M, Williams Middleton K. Venture creation programs: Bridging entrepreneurship education and technology transfer. *Education and Training*. 2015;57(1):48–73.
53. Lauritzen P, Reichard J, Ahmed S, Safa M. Review of non-destructive testing methods for physical condition monitoring in the port industry. *Journal of Construction Engineering*. 2019;2(2):103–11.
54. Lee S, Kalos N. Non-destructive testing methods in the US for bridge inspection and maintenance. *KSCE Journal of Civil Engineering*. 2014;18(5):1322–31.
55. Leydens JA, Lucena JC. *Engineering Justice: Transforming Engineering Education and Practice*. John Wiley & Sons; 2017.
56. Li H, Öchsner A, Hall W. Application of experiential learning to improve student engagement and experience in a mechanical engineering course. *European Journal of Engineering Education*. 2019;44(3):283–93.
57. Liew KM, Lei ZX, Zhang LW. Mechanical analysis of functionally graded carbon nanotube reinforced composites: A review. *Composite Structures*. 2015;120:90–7.
58. Liu Y. Renovation of a mechanical engineering senior design class to an industry-tied and team-oriented course. *European Journal of Engineering Education*. 2017;42(6):800–11.
59. Luan C, Movva S, Wang K, Yao X, Zhang C, Wang B. Towards next-generation fiber-reinforced polymer composites: A perspective on multifunctionality. *Functional Composites and Structures*. 2019;1(4):042002.
60. Mahesh V, Joladarashi S, Kulkarni SM. A comprehensive review on material selection for polymer matrix composites subjected to impact load. *Defence Technology*. 2021;17(1):257–77.
61. McBride MK, Worrell BT, Brown T, Cox LM, Sowan N, Wang C, et al. Enabling applications of covalent adaptable networks. *Annual Review of Chemical and Biomolecular Engineering*. 2019;10(1):175–98.
62. Melly SK, Liu L, Liu Y, Leng J. Active composites based on shape memory polymers: Overview, fabrication methods, applications, and future prospects. *Journal of Materials Science*. 2020;55:10975–11051.
63. Menard KP, Menard N. *Dynamic Mechanical Analysis*. CRC Press; 2020.
64. Mijumbi R, Serrat J, Gorricho JL, Bouten N, De Turck F, Boutaba R. Network function virtualization: State-of-the-art and research challenges. *IEEE Communications Surveys and Tutorials*. 2015;18(1):236–62.
65. Miranda J, Navarrete C, Noguez J, Molina-Espinosa JM, Ramírez-Montoya MS, Navarro-Tuch SA, et al. The core components of education 4.0 in higher education: Three case studies in engineering education. *Computers and Electrical Engineering*. 2021;93:107278.
66. Mirkouei A, Bhinge R, McCoy C, Haapala KR, Dornfeld DA. A pedagogical module framework to improve scaffolded active learning in manufacturing engineering education. *Procedia Manufacturing*. 2016;5:1128–42.
67. Mitra S, Ahire A, Mallik BP. Investigation of accelerated aging behaviour of high-performance industrial coatings by dynamic mechanical analysis. *Progress in Organic Coatings*. 2014;77(11):1816–25.
68. Moyné J, Iskandar J. Big data analytics for smart manufacturing: Case studies in semiconductor manufacturing. *Processes*. 2017;5(3):39.
69. Mullen E, Morris MA. Green nanofabrication opportunities in the semiconductor industry: A life cycle perspective. *Nanomaterials*. 2021;11(5):1085.
70. Najiha MS, Rahman MM, Yusoff AR. Environmental impacts and hazards associated with metal working fluids and recent advances in the sustainable systems: A review. *Renewable and Sustainable Energy Reviews*. 2016;60:1008–31.
71. Nascimento DLM, Alencastro V, Quelhas OLG, Caiado RGG, Garza-Reyes JA, Rocha-Lona L, et al. Exploring Industry 4.0 technologies to enable circular economy practices in a manufacturing context: A business model proposal. *Journal of Manufacturing Technology Management*. 2019;30(3):607–27.
72. Negendahl K. Building performance simulation in the early design stage: An introduction to integrated dynamic models. *Automation in Construction*. 2015;54:39–53.
73. Ojo AT, Lee PI. Applications of dynamic mechanical analysis in the engineering of amorphous solid dispersions. *Pharmaceutical Fronts*. 2020;2(1):e55–e63.
74. Osanov M, Guest JK. Topology optimization for architected materials design. *Annual Review of Materials Research*. 2016;46(1):211–33.
75. Ou R, Xie Y, Wang Q, Sui S, Wolcott MP. Material pocket dynamic mechanical analysis: A novel tool to study thermal transition in wood fibers plasticized by an ionic liquid (IL). *Holzforschung*. 2015;69(2):223–32.
76. Pamungkas SF, Widiastuti I, Suharno S. Kolb's experiential learning for vocational education in mechanical engineering: A review. In: *AIP Conference Proceedings*. AIP Publishing; 2019. Vol. 2114, No. 1.
77. Patra S, Ajayan PM, Narayanan TN. Dynamic mechanical analysis in materials science: The Novice's Tale. *Oxford Open Materials Science*. 2021;1(1):itaa001.
78. Pecoraro E, Pizzo B, Salvini A, Macchioni N. Dynamic mechanical analysis (DMA) at room temperature of archaeological wood treated with various consolidants. *Holzforschung*. 2019;73(8):757–72.
79. Plocher J, Panesar A. Review on design and structural optimisation in additive manufacturing: Towards next-generation lightweight structures. *Materials and Design*. 2019;183:108164.
80. Podgórski M, Spurgin N, Mavila S, Bowman CN. Mixed mechanisms of bond exchange in covalent adaptable networks: Monitoring the contribution of reversible exchange and reversible addition in thiol–succinic anhydride dynamic networks. *Polymer Chemistry*. 2020;11(33):5365–76.
81. Qian Q, Asinger PA, Lee MJ, Han G, Mizrahi Rodriguez K, Lin S, et al. MOF-based membranes for gas separations. *Chemical Reviews*. 2020;120(16):8161–8266.
82. Qin Z, Wu YT, Eizad A, Lyu SK, Lee CM. Advancement of mechanical engineering in extreme environments. *International Journal of Precision Engineering and Manufacturing-Green Technology*. 2021;1–16.
83. Rabal HJ, Braga Jr RA, editors. *Dynamic Laser Speckle*

- and Applications*. CRC Press; 2018.
84. Ramasesh RV, Browning TR. A conceptual framework for tackling knowable unknown unknowns in project management. *Journal of Operations Management*. 2014;32(4):190–204.
 85. Ramesh M, Palanikumar K, Reddy KH. Plant fibre-based bio-composites: Sustainable and renewable green materials. *Renewable and Sustainable Energy Reviews*. 2017;79:558–84.
 86. Rampal N, Ajenifuja A, Tao A, Balzer C, Cummings MS, Evans A, *et al.* The development of a comprehensive toolbox based on multi-level, high-throughput screening of MOFs for CO₂/N₂ separations. *Chemical Science*. 2021;12(36):12068–81.
 87. Ranjan R, Samant R, Anand S. Integration of design for manufacturing methods with topology optimization in additive manufacturing. *Journal of Manufacturing Science and Engineering*. 2017;139(6):061007.
 88. Ren S, Zhang Y, Liu Y, Sakao T, Huisingh D, Almeida CM. A comprehensive review of big data analytics throughout product lifecycle to support sustainable smart manufacturing: A framework, challenges, and future research directions. *Journal of Cleaner Production*. 2019;210:1343–65.
 89. Rubio F, Valero F, Llopis-Albert C. A review of mobile robots: Concepts, methods, theoretical framework, and applications. *International Journal of Advanced Robotic Systems*. 2019;16(2):1729881419839596.
 90. Saba N, Jawaid M. A review on thermomechanical properties of polymers and fibers reinforced polymer composites. *Journal of Industrial and Engineering Chemistry*. 2018;67:1–11.
 91. Safaei M, Foroughi MM, Ebrahimipour N, Jahani S, Omid A, Khatami M. A review on metal-organic frameworks: Synthesis and applications. *TrAC Trends in Analytical Chemistry*. 2019;118:401–25.
 92. Sreenivasan VS, Rajini N, Alavudeen A, Arumugaprabu V. Dynamic mechanical and thermo-gravimetric analysis of *Sansevieria cylindrica*/polyester composite: Effect of fiber length, fiber loading, and chemical treatment. *Composites Part B: Engineering*. 2015;69:76–86.
 93. Tao Q, Xu P, Li M, Lu W. Machine learning for perovskite materials design and discovery. *NPJ Computational Materials*. 2021;7(1):23.
 94. Tian L, Wang D, Wei Q. Study on dynamic mechanical properties of a nylon-like polyester tire cord. *Journal of Engineered Fibers and Fabrics*. 2019;14:1558925019868807.
 95. Tian W, Zhang S, Cui Z, Liu Z, Wang S, Zhao Y, *et al.* A fault identification method in distillation process based on dynamic mechanism analysis and signed directed graph. *Processes*. 2021;9(2):229.
 96. Tofail SA, Koumoulos EP, Bandyopadhyay A, Bose S, O'Donoghue L, Charitidis C. Additive manufacturing: Scientific and technological challenges, market uptake, and opportunities. *Materials Today*. 2018;21(1):22–37.
 97. Toor ZS. Space applications of composite materials. *Journal of Space Technology*. 2018;8(1):65–70.
 98. Urbina M, Rinaldi A, Cuesta-Lopez S, Sobetkii A, Slobozeanu AE, Szakalos P, *et al.* The methodologies and strategies for the development of novel material systems and coatings for applications in extreme environments—a critical review. *Manufacturing Review*. 2018;5.
 99. Wang S, Ma Y, Deng Z, Zhang S, Cai J. Effects of fused deposition modeling process parameters on tensile, dynamic mechanical properties of 3D printed polylactic acid materials. *Polymer Testing*. 2020;86:106483.
 100. Woldesenbet AK. Highway infrastructure data and information integration & assessment framework: A data-driven decision-making approach [doctoral dissertation]. Iowa State University; 2014.
 101. Yi XS, Du S, Zhang L. *Composite Materials Engineering, Volume 1: Fundamentals of Composite Materials*. Chemical Industry Press; 2018.
 102. Zhang H, Wang B, Xie A, Qi Y. Experimental study on dynamic mechanical properties and constitutive model of basalt fiber reinforced concrete. *Construction and Building Materials*. 2017;152:154–67.
 103. Zhou M, Wu Z, Ouyang X, Hu X, Shi C. Mixture design methods for ultra-high-performance concrete—a review. *Cement and Concrete Composites*. 2021;124:104242.
 104. Zobeiry N, Forghani A, Li C, Gordnian K, Thorpe R, Vaziri R, *et al.* Multiscale characterization and representation of composite materials during processing. *Philosophical Transactions of the Royal Society A: Mathematical, Physical and Engineering Sciences*. 2016;374(2071):20150278.